



BIP (Oldbury) Limited
A Member of the Tennant Group (Est. 1797)

Beetafin™ Polyurethane Dispersions



Beetafin Range

Reference	Type	TSC (%)	Cosolvent (%)	pH	Viscosity (cp)	100% Modulus (Mpa)	Tensile Strength (Mpa)	Elongation (%)	Hardness Koenig (sec)	Blocking Temp(°C)
BF2830	Anionic Aromatic Polyether	35	0%	8	100	1	5	1200	20	130
BF2797	Anionic Aliphatic Polyether	60	0%	8	200	1	15	1300	25	145
BF2825	Anionic Aliphatic Polyester	60	0%	8	200	2	30	1000	25	150
BF2833	Anionic Aliphatic Polyether	40	0%	8	100	2	10	1000	25	110
BF2837	Anionic Aliphatic Polyester	60	0%	8	200	2	40	1000	30	150
BF2820	Anionic Aliphatic Polyester	40	4.5% DPGDME	8	200	3	40	1000	30	120
BF2832	Anionic Aliphatic Polyether	40	0%	8	100	5	30	900	25	110
BF9075	Anionic Aliphatic Polyether	35	0%	8	300	10	60	600	90	110
BF2781	Anionic Aliphatic Polyester	38	0%	8	100	12	30	400	80	100
BF2800	Anionic Aliphatic Polyester	35	0%	8	100	15	50	550	90	130
BF2819	Anionic Aliphatic Polyester	30	5 % DPGDME	8	100	15	60	600	70	140
BF2815	Anionic Aliphatic Polyester	35	0.5% DPGDME	8	100	20	50	400	110	150
BF2817	Nonionic Aliphatic Polyether	45	0%	6	100	N/A	N/A	N/A	N/A	N/A
BF2808	Cationic Aliphatic Polyether	30	2% DPGDME	4	300	N/A	N/A	N/A	N/A	N/A

Beetafin Polyurethane Dispersion Application Guide

[illegible]

Beetafin TM Contact Information

Contacts

Sales: Tel: +44 (0)121 543 2051
Email: info@bip.co.uk

Technical: Tel: +44 (0)121 543 2062
Email: technical@bip.co.uk

Information and recommendations contained in this publication are to the best of our knowledge true and accurate. However since the conditions under which the products may be used are beyond our control, recommendations are made without warranty or guarantee. Typical properties recorded are based on test results for representative samples and are given as a guide and not as a specification for any particular property. BeetafinTM BIP and the BIP logo are the property of BIP (Oldbury) Limited.

BIP (Oldbury) Limited

Tat Bank Road, Oldbury, West Midlands, B69 4NH.
Telephone +44 (0)121 544 1555. Fax +44 (0)121 552 4267.
E-mail contact@bip.co.uk www.bip.co.uk